

Datasheet

Description:

AKROMID® A3 GF 25 3 black (3094) is a 25% glass fibre reinforced, nucleated polyamide 6.6 with high stiffness and strength

Applications

Mainly components in mechanical engineering and in the automotive industry

Typical values	Test specification	Method	Unit	Value d.a.m.
----------------	--------------------	--------	------	-----------------

Mechanical Properties

Tensile modulus	1 mm/min	ISO 527-2	MPa	8500
Stress at break	5 mm/min	ISO 527-2	MPa	160
Strain at break	5 mm/min	ISO 527-2	%	3
Flexural modulus	2 mm/min	ISO 178	MPa	6600
Flexural strength	2 mm/min	ISO 178	MPa	230
Flexural strain at break	2 mm/min	ISO 178	%	3,6
Charpy impact strength	23°C	ISO 179-1/1eU	kJ/m ²	50
Charpy impact strength	-30°C	ISO 179-1/1eU	kJ/m ²	45
Charpy notched impact strength	23°C	ISO 179-1/1eA	kJ/m ²	6
Izod notched impact strength	23°C	ISO 180/1A	kJ/m ²	6

Thermal Properties

Melting temperature	DSC, 10K/min	DIN EN 11357-1	°C	262
---------------------	--------------	----------------	----	-----

Flammability

Wall thickness			mm	0,4	0,8	1,6	2,0	3,2
Flammability		UL 94	class			HB		
Burning rate (< 100 mm/min)	> 1 mm thickness	FMVSS 302				+		

General Properties


Density	23°C	ISO 1183	g/cm ³	1,32
Content reinforcement/Content Filler		ISO 1172	%	25

Processing

Molding shrinkage	flow	ISO 294-4	%	0,15 - 0,35
Molding shrinkage	transverse	ISO 294-4	%	0,75 - 0,95

Continuation

Processing recommendations



ϑ_6	Drying time	h	0 - 4
ϑ_6	Drying temperature	°C	80
	Processing moisture	%	0,02 - 0,1
ϑ_1	Feed section	°C	60 - 80
ϑ_2	Section 1 - Section 4	°C	260 - 300
ϑ_3	Nozzle	°C	270 - 310
ϑ_4	Melt	°C	280 - 300
ϑ_5	Mould	°C	80 - 100
P_{Nach}	Holding pressure, spec.	bar	300 - 800
P_{Stau}	Back pressure, spez.	bar	50 - 150
	Injection speed		medium to high
	Screw speed	m/min	8 - 15

The listed values are recommendations. Higher values should be used for higher glass loadings. We recommend only de-humidifying or vacuum dryers. Extensive drying can cause filling problems and surface defects.