

PET – Polyethyleneterephthalate PET GF50

## PRECITE® E GF 50 black (7395)

Tensile modulus

**18000 MPa**

1 mm/min

ISO 527-2

Stress at break

**200 MPa**

5 mm/min

ISO 527-2

Charpy impact strength

**60 kJ/m<sup>2</sup>**

23°C

ISO 179-1/1eU

PRECITE® E GF 50 black (7395) is a 50% glass fibre reinforced, medium viscous polyethyleneterephthalate (PET) with very high stiffness and toughness as well as high dimensional stability and chemical resistance.

### Typical applications

Technical and precision parts in automobile, industrial, E/E and appliances industry. Metalsubstitution



### Mechanical Properties

Tensile modulus (1 mm/min   ISO 527-2) d.a.m.	18000 MPa
Stress at break (5 mm/min   ISO 527-2) d.a.m.	200 MPa
Strain at break (5 mm/min   ISO 527-2) d.a.m.	1,7 %
Charpy impact strength (23°C   ISO 179-1/1eU) d.a.m.	60 kJ/m <sup>2</sup>
Charpy notched impact strength (23°C   ISO 179-1/1eA) d.a.m.	11 kJ/m <sup>2</sup>



### Thermal Properties

Temperature of deflection under load HDT/A (1,8 MPa   ISO 75)	235 °C
Melt temperature (DSC, 10K/min   DIN EN 11357-1)	260 °C



### Flammability

Burning rate (UL 94) 0,8mm Wall thickness	HB Class
--	----------




### General properties

Density (23°C   ISO 1183)	1,75 g/cm <sup>3</sup>
---------------------------	------------------------

#### Disclaimer:

All specifications and information given on this website are based on our current knowledge and experience. A legally binding promise of certain characteristics or suitability for a concrete individual case cannot be derived from this information. The information supplied here is not intended to release processors and users from the responsibility of carrying out their own tests and inspections in each concrete individual case. AKRO®, AKROMID®, AKROLEN®, AKROLOY®, AKROTEK®, ICX® and PRECITE® are registered trademarks of the Feddersen Group.

Stress strain chart at 23°C



**Disclaimer:**


All specifications and information given on this website are based on our current knowledge and experience. A legally binding promise of certain characteristics or suitability for a concrete individual case cannot be derived from this information. The information supplied here is not intended to release processors and users from the responsibility of carrying out their own tests and inspections in each concrete individual case. AKRO®, AKROMID®, AKROLEN®, AKROLOY®, AKROTEK®, ICX® and PRECITE® are registered trademarks of the Feddersen Group.

PET – Polyethyleneterephthalate PET GF50

## PRECITE® E GF 50 black (7395)

### Processing information

The listed values are recommendations. Higher values should be used for higher glass loadings. We recommend only dehumidifying or vacuum dryers. Extensive drying can cause filling problems and surface defects.



⑥	Drying time	3 - 4 h
	Drying temperature ( $\tau \leq -30^\circ\text{C}$ )	120 - 140°C
	Processing moisture	$\leq 0,02\%$
①	Feed section	60 - 80°C
②	Temperature zone 1 - Zone 4	270 - 290°C
③	Nozzle temperature	270 - 295°C
④	Melt temperature	270 - 290°C
⑤	Mold temperature	130 - 160°C
→	Holding pressure, spec.	300 - 800 bar
←	Back pressure, spec.	30 - 100 bar
	Injection speed	medium to high
	Screw speed	8 - 15 m/min

### Warning

Due to hydrolysis sensitivity of polyesters, a careful drying of the material before processing is very important. High residual moisture contents causes, in addition to surface defects, a decomposition of the molecular chains and thus reduced mechanical properties. If there are longer interruptions of the process, the cylinder temperature should be lowered. Furthermore, we recommend a thorough cleaning of the screw cylinder with extended dwell time or a material change. Glass-fiber-reinforced polyolefins (PE, PP) have established a particularly good cleaning effect.

#### Disclaimer:

All specifications and information given on this website are based on our current knowledge and experience. A legally binding promise of certain characteristics or suitability for a concrete individual case cannot be derived from this information. The information supplied here is not intended to release processors and users from the responsibility of carrying out their own tests and inspections in each concrete individual case. AKRO®, AKROMID®, AKROLEN®, AKROLOY®, AKROTEK®, ICX® and PRECITE® are registered trademarks of the Feddersen Group.